

## TECHNICAL DATA SHEET

**Issue No**  
003/01

**Revision Date**  
01.07.2020

### Product

TECHNIC CCR120

### Classification

Modified Dicyclopentadiene Resin  
DCPD, Rosin Polymer  
Synthetic Resin  
Cut & Chip Resistance Resin  
Chunking & Chipping Resistance Resin  
Modified DCPD Resin

### Composition


Thermoplastic Resin from the polymerization of Dicyclopentadiene with Rosin

### Physical Properties

Property	Technic CCR120
Appearance	Flakes or Pastilles
Specific Gravity	1.07 (Typical)
Color	Dark Red to Reddish Brown
Softening Point	120 – 130 °C
Acid Value	5 – 20 mg KOH/g
Iodine value	115 – 135
Ash Content@ 750°C/2 h	0.5 % Max
Moisture content	0.7 % Max

### General Chemical Structure of Technic CCR120

#### Resins



### Applications

Technic CCR120 Resins are designed to improve the cutting, chunking and chipping resistance of tire treads. In rubber compounds, CCR resins could provide high tensile strength, high elongation at break, good dynamic stiffness and excellent tear strengths properties.

Other major usages are in Adhesives, such as Pressure-sensitive adhesives, Hot-melt adhesives, Coatings, Paints, Printing Inks and Rubber Compounds

### Storage:

The material can be stable for 24 months under the normal storage conditions. However, precautions must be taken to avoid exposure to sunlight and always, store the material in a sealed container under the dry and cool conditions.

Refer MSDS for more details

### Shelf Life

24 months from the date of manufacturing

#### Note:

Information in this publication is believed to be accurate and is given in good faith, but it is for the customer to satisfy itself of the suitability for its own particular purpose. TWPL gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that law prevents such exclusion.

**TECHNO WAXCHEM PVT. LTD.**

3C, Hitech Chambers, 84/1B, Topsia Road(S), Kolkata – 700 046, WB, India

Tel: +91 33 2285 1278 / 1279, 4004 8093 / 88094

Fax: +91 33 2285 1280. Email – [info@twc.in](mailto:info@twc.in). URL – [www.twc.in](http://www.twc.in)