

RUBBOND HM 100

TECHNICAL DATA SHEET

Issue No
002/02

Revision Date
17.07.2018

Product - Trade Name

RUBBOND HM100

Classification

Dry Bonding Agents – METHYLENE DONOR
Adhesion Promoter

Composition

Hexa Methoxy Methyl Melamine
Melamine Formaldehyde Resin
Methylated Melamine Formaldehyde Resin
Modified Melamine Formaldehyde Resin

Physical properties

Form : Clear Liquid.
Sp. Gr. @ 25°C : 1.20 +/- 0.05

Chemical properties

Total Solids (%)	98 min
Moisture content (%)	2.0 max
Refractive Index Q 20°C	1.510 – 1.530
Free Formaldehyde (%)	0.2 maximum
Nitrogen content	21.5 – 24.0

Processing behavior

It is safe in processing both non-black & black reinforced compounds.

Recommended Dosage

RUBBOND HM100 : 2 – 3 Phr
Resorcinol Donor : 3 – Phr

Advantages

- Easy Handling
- Easy Dispersion in compound
- Non corrosive effects on coated steel
- Non dusting
- Scorch protection higher than HMT
- Non-toxic and no skin irritation

Principally used as a component of Dry Bonding Agent.
It is recommended for use in final mix in case of two stage mixing.

Application

RUBBOND HM100 has been successfully designed to meet the stringent needs of cord-rubber properties of tyre and non - tyre industries. It offers a balanced combination of good adhesion and excellent fatigue resistance in conjunction with Methylene acceptors like TECHNIC B19S / B20S through formation of an in-situ resin. The recommended dosage above shows the level for initial evaluations.

Handling precautions

Irritating to the eyes, respiratory system and skin. Avoid contact with eyes, skin and clothing. Wash thoroughly after handling.
Refer MSDS for complete details

Packaging

200/250 kgs in MS/HDPE drums

Storage properties

Stable for one year, when stored tightly at normal room temperature.

Shelf Life

12 months from the date of manufacturing.

Note:

Information in this publication is believed to be accurate and is given in good faith, but it is for the customer to satisfy itself of the suitability for its own particular purpose. RCPL gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that law prevents such exclusion. Implied warranty or condition (statutory or otherwise) is excluded except to the extent that law prevents such exclusion.

RAJSHA CHEMICALS PRIVATE LIMITED

www.twc.in

Works:

Block No.: 637, Lamdapura Road, At. Manjisar
PO: Lamdapura, Ta: Savli, Dist. Vadodara 391 775, India
Tel – +91 9662049271
Email – office@rajsha.com

Head Office:

3C Hi Tech Chambers, 84/1B Topsia Road (S)
Kolkata 700 046, West Bengal, India
Tel – 2285 1278 / 1279. Fax - +91 33 2285 1280
E mail – info@twc.in