

TECHNICAL DATA SHEET

Issue No
003/01

Revision Date
01.07.2020

Product Name

TECHNIC B22Z

Classification

Dry Bonding Agents.
Styrenated Resorcinol Formaldehyde Resin
Resorcinol Donor / Methylene Acceptor
Formaldehyde, polymer with 1,3-benzenediol and ethenylbenzene

Composition

Styrenated Resorcinol Formaldehyde Polymer

Physical Properties

Form : Pastilles
Colour : Dark Red - Brown
Specific Gravity @ 25°C : 1.20 +/- 0.03

Chemical Properties

Softening Point (°C) : 100 – 110
PH (50% alcohol solⁿ) : 4.0 – 6.0
Moisture Content : 0.7% max
Ash Content @ 850°C/1hr : 0.1% max
Free Resorcinol Content : 0.1% max

Solubility

Water : Insoluble
Alcohol : Completely soluble
Ketones : Completely soluble
Aromatic Solvents : Insoluble

Storage Properties

TECHNIC B22Z is comparatively very less hygroscopic in comparison to other resorcinol formaldehyde resin. Although for best results it must be protected from exposure to relative humidity. The resin should be stored in a cool dry place. The resin is stable for one year in protected as per directions above.

Processing Behavior

It is safe in processing.

Recommended Dosage

Between 3 to 4 phr is normally recommended for the Dry Bonding System.

Advantages

TECHNIC B22Z is a reaction product of formaldehyde with resorcinol, resorcinol polymers and styrene. It is supplied in pastille form. It has low vapour pressure, thus, the fuming and weight loss that occur with processing resorcinol at temperatures above 150°C is substantially reduced with the usage of TECHNIC B22Z

Technological Properties (Usage)

TECHNIC B22Z can be used as a resorcinol component of the Dry Bonding system for adhesion of synthetic tyre cord and brass plated tyre cord to rubber. It offers a balanced combination of good adhesion and excellent flex fatigue resistance in conjunction with methylene donors like formaldehyde, Hexamethylenetetramine and Hexamethoxymethylolmelamine Resin through formation of an in – situ resin. The product contains nil formaldehyde.

Handling precaution

Standard protective equipment to avoid contact with Skin and eyes should be used during handling. May be Irritating to eyes and skin. Washing with plenty of water is advised to be followed by a medical check up. Refer MSDS for more details

Packaging

Packed in 25 kg net weight HDPE laminated kraft paper bag

Shelf Life

The resin is stable for 2 (two) years from the date manufacturing. It should be stored under recommended conditions.

Note:

Information in this publication is believed to be accurate and is given in good faith, but it is for the customer to satisfy itself of the suitability for its own particular purpose. Techno Products India gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that law prevents such exclusion.

TECHNO WAXCHEM PVT. LTD.

3C, Hitech Chambers, 84/1B, Topsia Road(S), Kolkata – 700 046, WB, India

Tel: +91 33 2285 1278 / 1279, 4004 8093 / 88094

Fax: +91 33 2285 1280. Email – info@twc.in. URL – www.twc.in