



RUBBOND® 40

TECHNICAL DATA SHEET

Issue No
002/05

Revision Date
01.10.2022

Product - Trade Name

RUBBOND® 40

Classification

A blend of dark aromatic hydrocarbon resins
Homogenizing Agent

Physical Properties

Form : Pastilles
Appearance : Black Pastilles
Sp. Gr. @ 25C : 1.04 ± 0.04

Chemicals Properties

Product	RUBBOND® 40
Softening Point (°C, R&B) 5°C/Minute	96 - 110
Ash content (% , Max)750 °C/2hrs	2 Max.

Applications

RUBBOND® 40 homogenizing agent enhances the homogeneity of elastomers of dissimilar polarity and viscosity. During mixing process, RUBBOND® 40 can be rapidly absorbed by the polymers. The homogenizing agents are particularly effective with those elastomer blends, which tend to deteriorate at the beginning of the mixing cycle.

During vulcanization process, RUBBOND® 40 does not harden. The hardness of the vulcanization is not reduced as much as when using, for example, mineral oil plasticizers.

The reduction of compound viscosity and daring achieved with RUBBOND® 40 assists downstream processing. For occasion, bagging tendency can be reduced, extrusion rates are increased without increasing die swell and calendaring properties are improved. These benefits are retained even after long storage periods of the green compound.

Advantages

RUBBOND® 40 improves mold flow and extrusion characteristics. Reduces nerve and shrinkage. Improves homogeneity of elastomers and fillers. Reduces mixing cycle time, energy consumption, and viscosity. Enhances green tack.

Storage

Stable for one year, when stored at ambient temperature in original sealed container & in well ventilated place.

Shelf Life

1 Year from the date of manufacture

Packaging

25 kg (Net Wt) in Bags / Cartons

Health and Safety Information

Before handling this material Refer to the Material Refer MSDS for complete details

REACH Compliance:

Material is meeting the REACH compliance.

Note:

Information in this publication is believed to be accurate and is given in good faith, but it is for the customer to satisfy itself of the suitability for its own particular purpose. RCPL gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that law prevents such exclusion.

RAJSHA CHEMICALS PRIVATE LIMITED

www.twc.in

Works:

Block No.: 637, Lamdapura Road, At. Manjusar
PO: Lamdapura, Ta: Savli, Dist. Vadodara 391 775, India
Tel – +91 9662049271
Email – office@rajsha.com

TWC Group, Corporate Office:

Hi Tech Chambers, 5th Floor, 84/1B Topsis Road (S)
Kolkata 700 046, India
Tel – +91 33 2285 1278 / 1279. Fax - +91 33 2285 1280
E mail – info@twc.in