



# TERPERES® - SA85

## TECHNICAL DATA SHEET

**Issue No**  
001/04

**Issue Date**  
01.12.2022

### Product - Trade Name

TERPERES®- SA85

### Classification

Poly (Alpha-Methyl Styrene) Resin (PAMS)

### Physical properties:

Parameter	Specification
Physical Form	Pastilles / Flakes
Colour	Transparent/Light Yellow

### Chemical Properties:

Parameter	Specification	Test Method
Sp. gravity@25 °C	1.10±0.05	D1817
Loss on Heating, % (@105C,1 Hr.)	1.0 Max	D4571
Ash Content, % (@ 750 °C,1Hr.)	0.10 Max	D4574
Softening Point, °C (Ring & Ball 5°C/min)	85±5	D6493
Glass Transition Temp., °C	38±5	D6604

### Solubility

TERPERES® - SA85 is

- Soluble in aromatic solvents like Toluene Ketones and esters like acetone.
- Insoluble in aliphatic solvents and Alcohol.

### Advantages

- Aromatic hydrocarbon resin with superior oxidative stability.
- Heat Resistance
- Rubber Processing
- Improved Strength

### Application

- Rubber – Tire manufacturing
- Paper – Packaging & Book binding
- Non-woven
- Wood-working

### Compatibility

- Styrene phase of SBCs
- Paraffin, Micro-crystalline, Polyethylene, & Fischer-Tropic Waxes
- EVAs when blended with other resins like rosin esters or AMS Phenolic

### Handling & Storage

Need to store in tight containers away from heat and humidity.

### Packaging

25 kg in Carton packing.

### Shelf Life

Stable for 12 months from the date of manufacturing.

### REACH Compliance:

Material is meeting the REACH compliance.

### Note:

Information in this publication is believed to be accurate and is given in good faith, but it is for the customer to satisfy itself of the suitability for its own particular purpose. RCPL gives no warranty as to the fitness of the product for any particular purpose and any implied warranty or condition (statutory or otherwise) is excluded except to the extent that law prevents such exclusion.

**RAJSHA CHEMICALS PRIVATE LIMITED**

[www.twc.in](http://www.twc.in)

### Works:

Block No.: 637, Lamdapura Road, At. Manjusar  
Road (S) PO: Lamdapura, Ta: Savli, Dist. Vadodara 391 775, India  
Tel – +91 9662049271  
Email – [office@rajsha.com](mailto:office@rajsha.com)

### TWC Group, Corporate Office:

Hi Tech Chambers, 5<sup>th</sup> Floor, 84/1B Topsia  
Kolkata 700 046, India  
Tel – +91 33 2285 1278 / 1279. Fax - +91 33 2285 1280  
E mail – [info@twc.in](mailto:info@twc.in)