



# RUBBOND® RR 100H

## TECHNICAL DATA SHEET

**Issue No**  
001/01

**Revision Date**  
01.12.2022

**Product**  
RUBBOND® RR100H

**Classification**  
Reinforcing Phenolic Resin  
Reinforcing Phenol Formaldehyde Resin with Hexa Methylene Tetramine

**Composition**  
Phenol – formaldehyde (PF) resins with Hexa Methylene Tetramine

### Physical properties

Parameter	Specification
Physical Form	Light to Tan Powder

### Chemical Properties

Parameter	Specification	Test Method
Melting Point (°C)	80 - 90	D1519
HMT Content (%)	9 - 11	IS4306, RCPL T-07
Norton Flow @ 125°C (mm)	30 - 50	RCPL T-34
Gel Time @ 150°C (Sec)	20 - 40	D3532/ D4640
Volatile matter @160°C,2Hrs, (%)	Max. 5	D4571
Ash Content @ 900 °C,2Hrs (%)	Max. 1	D4574

### General Recommendations

Recommended for use in SBR Rubber. Compatible in SBR Rubber to the extent of 10-15 parts per hundred. This amount of resin will act as an effective plasticizer during processing and will contribute strongly to hardness, stiffness and abrasion resistance after cure.

The compatibility of RR 100H with SBR Rubber can be greatly increased by using Nitrile Rubber in the formulation. The Nitrile Rubber services as a common solvent or flux.

These recommendations also apply to Natural Rubber and EPDM, and to their blends with SBR. As with most phenolics, RR 100H is fully compatible with Nitriles.

### Use in Rubber Compounds

RUBBOND® RR100H resin should be used in the rubber compounding applications. In order to achieve an optimum reinforcement in rubber compounds, these reinforcing resins should be added at a level of about 5 - 15 weight %.

### Health and Safety Information

Before handling this material:

- Refer to the Safety Data Sheet (SDS) prior to use
- Wear gloves, safety glasses and dust masks
- In the case of skin contact, wash with soap and water.

### Packaging

25 Kgs in HDPE laminated paper bags

### Storage

Store in a cool and dry storage area in original sealed container

### Shelf Life

12 Months from the date of manufacture under the normal storage conditions

### REACH Compliance:

Material is meeting the REACH compliance.

**IMPORTANT!** The information presented herein, while not guaranteed, was prepared by technical personnel and is true and accurate to the best of our knowledge. No warranty or guaranty, express or implied is made regarding performance stability or otherwise. This information is not intended to be all inclusive as the manner and conditions of use, handling, storage and other factors may involve other and additional safety and performance considerations. While our technical personnel will be happy to respond to questions regarding safe handling and use procedures, safe handling and use remains the responsibility of the customer.

RAJSHA CHEMICALS PRIVATE LIMITED

[www.twc.in](http://www.twc.in)

**Works:**  
Block No.: 637, Lamdapura Road, At. Manjusar  
PO: Lamdapura, Ta: Savli, Dist. Vadodara 391 775, India  
Tel – +91 9662049271  
Email – [office@rajsha.com](mailto:office@rajsha.com)

**TWC Group, Corporate Office:**  
Hi Tech Chambers, 5<sup>th</sup> Floor, 84/1B Topsia Road (S)  
Kolkata 700 046, India  
Tel – +91 33 2285 1278 / 1279. Fax - +91 33 2285 1280  
E mail – [info@twc.in](mailto:info@twc.in)